

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-173140

(43)Date of publication of application : 26.06.1998

(51)Int.Cl. H01L 27/10
 H01L 27/04
 H01L 21/822
 H01L 27/108
 H01L 21/8242
 H01L 21/8247
 H01L 29/788
 H01L 29/792

(21)Application number : 08-351916

(71)Applicant : TEXAS INSTR JAPAN LTD


(22)Date of filing : 11.12.1996

(72)Inventor : AOKI KATSUHIRO
 MURAYAMA IKUKO
 FUKUDA YUKIO
 NUMATA KEN
 NISHIMURA AKITOSHI

(54) MANUFACTURE OF FERROELECTRIC CAPACITOR AND MANUFACTURE OF FERROELECTRIC MEMORY DEVICE

(57)Abstract:

PROBLEM TO BE SOLVED: To form a high-quality ferroelectric thin film by forming excellent crystal nuclei by depositing a metallic or metal oxide thin film, a metal oxide material, and a ferroelectric material by sputtering, etc.
 SOLUTION: After an Ir thin film 6 is formed on a silicon oxide film 10 formed on an Si substrate 1, a Ti film 31 is deposited on the Ir thin film 6 at a room temperature. Then a PbTiO₃ film 33 is formed as crystal nuclei by depositing PbO 32 on the Ti film 31 by sputtering using a PbO ceramic target at a temperature higher than the crystallization temperature of PbTiO₃ and a Pb(Ti, Zr)O₃ thin film 17 is deposited on the film 33 by sputtering Pb(Ti, Zr)O₃ 34. Since the formed PbTiO₃ film 33 becomes perovskite crystal nuclei, the particles 17A of the deposited Pb(Ti, Zr)O₃ thin film 17 grow in columnar shapes and excellently deposit due to the crystal nuclei of the base film 33.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision
of rejection]

[Date of requesting appeal against examiner's
decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2000 Japanese Patent Office